



Radiata – AU - KD Sawn NST Grade

Species: pinus radiata - radiata pine – from Australia
Thickness: 38, 50mm
Width: 100, 150mm
Lengths: 1.2m – 6.0m
Tolerances: thickness +/- 2mm widths +/- 3mm
Finish Sawn
Moisture: Up to 16%
Wane: Mostly without wane (limited to 10%)
Pith: Will contain pith

All other natural occurring defects including distortion are allowable

Log source: Typically cut from the centre of the log with HI (Heart In)

Typical applications Pallets, packaging, formwork, bins, crates, economical furniture components

Note: As timber is a natural resource some variation is typical, it is however expected that a minimum of 95% of each pack will be within the tolerances specified herewith.



